

536-1255 ora Verde® Bianco PU Basecoat Neutral

| | |
|--------------------------------|---|
| Product codes: 536-1255 | Viscosity Zahn #3 signature cup 45 sec at 77°F |
| | Flash Point: 21°F |
| | Density (lb/gal): 10.5 |
| | Solid (% by weight): 58% |
| | Solid (% by volume): 39% |
| | Shelf Life (months): 12 |

Product Description:

Bianco is our pigmented polyurethane system; Bianco PU Basecoat Neutral is a universal primer designed to be used in conjunction with our ora Verde® line topcoats. Durable and flexible, it can be used as tinted primer to achieve deep, dark and rich colors. Builds quickly to help you achieve a high end look when your need is for an opaque color.

Uses:

Developed for use in the high end kitchen cabinet market. Its durability will also allow for use in store fixture applications.

| | |
|--|-------------------------------------|
| Environmental Data (as supplied): | VOC less exempt lb/gal: <4.4 |
| | VOC lb/gal: <4.4 |
| | VOC less exempt g/l: |
| | VOC g/l: |
| | VOC lb/lb Solid: <0.72 |
| | VHAPs lb/lb Solid: <0.17 |

Note:
N/A

| | |
|-------------------------|--|
| Application Data | Suggested Uses: Wood Finish |
| | Mixing Ratio: 100 Parts 536-1255 with 50 Parts 876-9068 (by volume) |
| | Suggested Uses: 2 Hours |
| | Application Viscosity: Zahn #2 signature cup 30 seconds |
| | Reducer: Fast 803-1410, Medium 803-1409, or slow 803-1408 if needed |
| | Retarder: 800-5328 3-5% by volume |
| | Clean-up Solvent: 800-5500 Acetone |
| | Recommended Wet Film: 3 to 5 wet mils |
| | Coverage: N/A |

Note:
MAXIMUM DRY FILM THICKNESS OF THE SYSTEM MUST NOT EXCEED 6.0 DRY MILS

Directions for use:

Surface Preparation:

Substrate must be sanded using 120, 150 or 180 grit paper prior to priming. Basecoat should be sanded with 280/320 grit paper prior to being coated. The Basecoat should be coated within eight hours of being sanded. Appropriate topcoat is the ora Verde Bianco 109-48XX, or ora Verde Chiaro 436-48XX. When recoating, the previous coat must be sanded and the next coat applied within eight hours.

General Information:

The mixed product contains 876-9068, an isocyanate based co-reactant. Please follow all precautions associated with handling and use of those materials. Refer to MSDS for detailed information.

Product must be thoroughly stirred before adding the hardener in the recommended ratio. The viscosity of the product should be monitored after mixing with the hardener.

The relative humidity in the application and drying room must not exceed 75% for maximum coating performance. The hardener must not be exposed to water or solvents containing alcohol.

THE CUSTOMER IS RESPONSIBLE FOR FOLLOWING THE RECOMMENDED APPLICATION PROCEDURES. FAILURE TO ADHERE TO THE RECOMMENDATIONS GIVEN IN THIS DATA SHEET WILL LIKELY RESULT IN UNSATISFACTORY FILM APPEARANCE OR FILM FAILURE. THE COMPLETE COATING SYSTEM SHOULD BE CHECKED FOR REQUIRED PROPERTIES PRIOR TO THE START-UP OF PRODUCTION

Drying Times:

| | Room Temperature (20°C / 68°F) | Forced Drying Schedule (50°C / 122°F) |
|------------------------|---|--|
| Tack Free Time: | 20 minutes | 10 minutes @ room temperature |
| Dry to Sand: | 2 hours | 24 hours |
| Dry to Stack: | 15 minutes @ 110°F | 15 minutes @ 140°F |

Note:

N/A

Dry times are greatly affected by film build, porosity of substrate, air movement as well as heat and humidity. Temperatures are based on actual board temperature. This may vary depending on length of time for boards to reach these temperatures. Minimum curing temperatures of 64°F/18°C must be maintained throughout the curing cycle to achieve the film integrity as stated in product features.

These products are designed for industrial use only. AkzoNobel views safety as a top priority. Please refer to Material Safety Data Sheet for information on the safe use of this product.

Values shown are calculated estimates and should not be construed as product specifications. We cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and users assume all responsibility and liability for loss or damage arising from the use of our products whether used alone or a combination with other products. Use of unapproved or reclaimed solvent blends may reduce film properties and is not recommended.

Akzo Nobel Coatings, Inc
1431 Progress Ave
High Point, NC 27260
336-841-5111

Updated: 2024-05-18 01:00:42

Copyright 2021 AkzoNobel. All Rights Reserved. Chemcraft is a registered trademark of Akzo Nobel Coatings Inc.