

109-58XX ora Verde® Acrilico White PU TC

| | | | |
|-----------------------|-----------------------------|------------------|--------------------------------------|
| Product codes: | 109-5805 Flat | Viscosity | Zahn #2 signature cup 40 sec at 77°F |
| | 109-5820 Low Gloss | | |
| | 109-5835 Satin | | |
| | 109-5850 Semi-Gloss | | |
| | 109-5870 Gloss | | |
| | Flash Point: | | 39.2 °F |
| | Density (lb/gal): | | 9.09 |
| | Solid (% by weight): | | 38.56% |
| | Solid (% by volume): | | 24.10% |
| | Shelf Life (months): | | 12 |

Product Description:

Acrilico White has high durability and is formulated as a low yellowing white topcoat with good light fastness. Acrilico White takes acrylic polyurethane coatings to a new level. It is known for its luster, silky smooth feel and overall aesthetics. The Acrilico line provides superior surface and chemical resistance. The Acrilico White is the logical choice for the high end woodworking.

Uses:

Acrilico White is designed for use on high end woodwork such as: cabinetry, furniture, restaurants/bars, business jet interior, luxury ship interior, etc.

Environmental Data (as supplied):

| | |
|--------------------------------|------|
| VOC less exempt lb/gal: | <5.6 |
| VOC lb/gal: | <5.6 |
| VOC less exempt g/l: | <675 |
| VOC g/l: | <675 |
| VOC lb/lb Solid: | <1.6 |
| VHAPs lb/lb Solid: | <0.3 |

Note:

N/A

Application Data

| | |
|-------------------------------|--|
| Suggested Uses: | Wood Finish |
| Mixing Ratio: | 100 Parts 109-58XX with 20 Parts 876-9101 (by volume) |
| Suggested Uses: | 6 hours |
| Application Viscosity: | Zahn #2 signature cup 38 - 42 seconds |
| Reducer: | Fast 803-1410, Medium 803-1409, or slow 803-1408 if needed |
| Retarder: | 800-5328 3 - 5% by volume |
| Clean-up Solvent: | 800-5500 Acetone |
| Recommended Wet Film: | 3 to 5 wet mils |
| Coverage: | N/A |

Note:

MAXIMUM DRY FILM THICKNESS OF THE SYSTEM MUST NOT EXCEED 6.0 DRY MILS

Directions for use:

Surface Preparation:

Substrate must be sanded using 120, 150 or 180 grit paper prior to staining or coating. Primer should be sanded with 280/320 grit paper prior to being coated. The primer should be coated within eight hours of being sanded. Appropriate primer is the ora Verde® Bianco PU Basecoat White 536-1208 or 536-1253. When recoating, the previous coat of Acrilico White must be sanded and the next coat applied within eight hours.

General Information:

The mixed product contains 876-9101, an isocyanate based co-reactant. Please follow all precautions associated with handling and use of those materials. Refer to MSDS for detail information.

Product must be thoroughly stirred before adding the hardener in the recommended ratio. The viscosity of the product should be monitored after mixing with the hardener.

The relative humidity in the application and drying room should not exceed 75% for maximum coating performance.

THE CUSTOMER IS RESPONSIBLE FOR FOLLOWING THE RECOMMENDED APPLICATION PROCEDURES. FAILURE TO ADHERE TO THE RECOMMENDATIONS GIVEN IN THIS DATA SHEET WILL LIKELY RESULT IN UNSATISFACTORY FILM APPEARANCE OR FILM FAILURE. THE COMPLETE COATING SYSTEM SHOULD BE CHECKED FOR REQUIRED PROPERTIES PRIOR TO THE START-UP OF PRODUCTION

Drying Times:

| | Room Temperature (20°C / 68°F) | Forced Drying Schedule (50°C / 122°F) |
|------------------------|---|--|
| Tack Free Time: | 15 minutes | 15 minutes |
| Dry to Sand: | 4 hours | 24 hours |
| Dry to Stack: | 15 minutes | 15 minutes |

Note:

N/A

Dry times are greatly affected by film build, porosity of substrate, air movement as well as heat and humidity. Temperatures are based on actual board temperature. This may vary depending on length of time for boards to reach these temperatures. Minimum curing temperatures of 64°F/18°C must be maintained throughout the curing cycle to achieve the film integrity as stated in product features.

These products are designed for industrial use only. AkzoNobel views safety as a top priority. Please refer to Material Safety Data Sheet for information on the safe use of this product.

Values shown are calculated estimates and should not be construed as product specifications. We cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and users assume all responsibility and liability for loss or damage arising from the use of our products whether used alone or a combination with other products. Use of unapproved or reclaimed solvent blends may reduce film properties and is not recommended.

Akzo Nobel Coatings, Inc
1431 Progress Ave
High Point, NC 27260
336-841-5111

Updated: 2024-05-10 01:34:37

Copyright 2021 AkzoNobel. All Rights Reserved. Chemcraft is a registered trademark of Akzo Nobel Coatings Inc.