

441-21XX Chemlack NC Clear TC

Product codes:	441-2135 Satin	Viscosity	Zahn #2 signature cup 25 sec at 77°F
	441-2150 Semi-Gloss	Flash Point:	-4°F (-20°C)
	441-2190 High Gloss	Density (lb/gal):	7.75
		Solid (% by weight):	25%
		Solid (% by volume):	19%
		Shelf Life (months):	12

Product Description:

441-21XX Chemlack Topcoat is a scratch resistant, single component nitrocellulose lacquer that provides good depth and a nice, smooth surface. Chemlack provides good clarity as a nitrocellulose topcoat. This product dries rapidly and has a smooth feel when fully cured.

Uses:

441-21XX Chemlack Topcoat can be used for many interior wood applications as a high quality nitrocellulose lacquer.

Environmental Data (as supplied):

VOC less exempt lb/gal:	<5.75
VOC lb/gal:	<5.35
VOC less exempt g/l:	<685
VOC g/l:	<645
VOC lb/lb Solid:	<2.8
VHAPs lb/lb Solid:	<0.8

Note:

N/A

Application Data

Suggested Uses:	Wood Finish
Mixing Ratio:	N/A
Pot Life:	N/A
Application Viscosity:	Zahn #2 signature cup 20 – 25 seconds
Reducer:	803-1395
Retarder:	5% 803-1393 or 800-5328
Clean-up Solvent:	803-1395
Recommended Wet Film:	3 – 5 mils
Coverage:	293 sq. ft/gal at 1 mil dry and at 100% transfer efficiency. Coverage will vary depending on method of application or coating thickness.

Note:

N/A

Directions for use:

Surface Preparation:
Substrate must be sanded using 120, 150 or 180 grit stearated paper prior to staining or coating. Sealers should be sanded with 240, 280 and 320 grit stearated papers prior to being coated.

General Information:
441-21XX Chemlack Topcoat may be applied in two or more coats, depending on the desired finish. The dry film build of the total coating system should not exceed 4 mils.
THE CUSTOMER IS RESPONSIBLE FOR FOLLOWING THE RECOMMENDED APPLICATION PROCEDURES. FAILURE TO ADHERE TO THE RECOMMENDATIONS GIVEN IN THIS DATA SHEET WILL LIKELY RESULT IN UNSATISFACTORY FILM APPEARANCE OR FILM FAILURE. THE COMPLETE COATING SYSTEM SHOULD BE CHECKED FOR REQUIRED PROPERTIES PRIOR TO THE START-UP OF PRODUCTION

Drying Times:

	Room Temperature (68°F)	Forced Drying Schedule (122°F)
Tack Free Time:	5 – 10 minutes	Flash off before entering oven
Dry to Sand:	10 – 15 minutes	3 – 5 minutes
Dry to Stack:	3 hours	20 – 30 minutes

Note:
N/A

Dry times are greatly affected by film build, porosity of substrate, air movement as well as heat and humidity. Temperatures are based on actual board temperature. This may vary depending on length of time for boards to reach these temperatures. Minimum curing temperatures of 64°F/18°C must be maintained throughout the curing cycle to achieve the film integrity as stated in product features.

These products are designed for industrial use only. AkzoNobel views safety as a top priority. Please refer to Material Safety Data Sheet for information on the safe use of this product.

Values shown are calculated estimates and should not be construed as product specifications. We cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and users assume all responsibility and liability for loss or damage arising from the use of our products whether used alone or a combination with other products. Use of unapproved or reclaimed solvent blends may reduce film properties and is not recommended.

Akzo Nobel Coatings, Inc
1431 Progress Ave
High Point, NC 27260
336-841-5111