

109-46XX Selva™ Pro Acrilico Neutral Acrylic Topcoat

| | | | | |
|-----------------------|---------------------|-----------------------------|--|-------|
| Product codes: | 109-4605 Flat | Viscosity | Zahn #2 signature cup 30-34 sec at 25° C | |
| | 109-4610 Matte | | | |
| | 109-4625 Low Gloss | | Flash Point: | 10° C |
| | 109-4635 Satin | | Density (kg/l): | 0.96 |
| | 109-4650 Semi-Gloss | | Solid (% by weight): | 33.6 |
| | 109-4690 High Gloss | | Solid (% by volume): | 26.7 |
| | | Shelf Life (months): | 24 | |

Product Description:

Acrilico Neutral Acrylic Topcoat has high durability and is formulated as a non-yellowing topcoat with good light fastness. Acrilico Neutral takes acrylic polyurethane coatings to a new level. It is known for its luster, silky smooth feel and overall aesthetics. The Acrilico line provides superior surface and chemical resistance. Selva Pro Acrilico is the logical choice for the high end woodworking market.

Uses:

Developed for use in the high end kitchen cabinet market. Its durability will also allow for use in store fixture applications.

| | | |
|--|-----------------------------|-----|
| Environmental Data (as supplied): | VOC less exempt g/l: | 671 |
| | VOC g/l: | 671 |

Note:

N/A

| | | |
|-------------------------|-------------------------------|---|
| Application Data | Suggested Uses: | Wood Finishes |
| | Mixing Ratio: | 100 Parts 109-46XX with 10 Parts 876-9102 (by volume) |
| | Suggested Uses: | 4 hours |
| | Application Viscosity: | Zahn #2 signature cup 22-25 seconds. |
| | Reducer: | 803-2000 |
| | Retarder: | 800-2001 3-5% by volume |
| | Clean-up Solvent: | 800-5500 Acetone |
| | Recommended Wet Film: | 4-6 wet mils |
| | Coverage: | N/A |

Note:

MAXIMUM DRY FILM THICKNESS OF THE SYSTEM MUST NOT EXCEED 6 DRY MILS

Directions for use:

Surface Preparation:

Substrate must be sanded using 120, 150 or 180 grit paper prior to priming. Primer should be sanded with 280/320 grit paper prior to being coated, The Primer should be coated within eight hours of being sanded. Appropriate primers are the Selva Pro 536-1700, 536-1701, or 536-1702. When recoating, the previous coat of Acrilico must be sanded and the next coat applied within eight hours.

General Information:

The mixed product contains 876-9102, an isocyanate based co-reactant. Please follow all precautions associated with handling and use of those materials. Refer to MSDS for detail information. Oil stains must be avoided because they will interfere with the adhesion.

Product must be thoroughly stirred before adding the hardener in the recommended ratio. The viscosity of the product should be monitored after mixing with the hardener. The relative humidity in the application and drying room should not exceed 75% for maximum coating performance.

THE CUSTOMER IS RESPONSIBLE FOR FOLLOWING THE RECOMMENDED APPLICATION PROCEDURES. FAILURE TO ADHERE TO THE RECOMMENDATIONS GIVEN IN THIS DATA SHEET WILL LIKELY RESULT IN UNSATISFACTORY FILM APPEARANCE OR FILM FAILURE. THE COMPLETE COATING SYSTEM SHOULD BE CHECKED FOR REQUIRED PROPERTIES PRIOR TO THE START-UP OF PRODUCTION

Drying Times:

| | Room Temperature (20°C / 68°F) | Forced Drying Schedule (50°C / 122°F) |
|------------------------|---|--|
| Tack Free Time: | 15 minutes | 10 minutes |
| Dry to Sand: | 4 hours | 30 minutes |
| Dry to Stack: | 24 hours | 1 hour |

Note:

N/A

Dry times are greatly affected by film build, porosity of substrate, air movement as well as heat and humidity. Temperatures are based on actual board temperature. This may vary depending on length of time for boards to reach these temperatures. Minimum curing temperatures of 64°F/18°C must be maintained throughout the curing cycle to achieve the film integrity as stated in product features.

These products are designed for industrial use only. AkzoNobel views safety as a top priority. Please refer to Material Safety Data Sheet for information on the safe use of this product.

Values shown are calculated estimates and should not be construed as product specifications. We cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and users assume all responsibility and liability for loss or damage arising from the use of our products whether used alone or a combination with other products. Use of unapproved or reclaimed solvent blends may reduce film properties and is not recommended.

Akzo Nobel Coatings, Inc
1431 Progress Ave
High Point, NC 27260
336-841-5111

Updated: 2024-11-07 01:00:44

Copyright 2021 AkzoNobel. All Rights Reserved. Chemcraft is a registered trademark of Akzo Nobel Coatings Inc.