

## 117-27XX CHEMLIFE® 24 PLUS CV Clear Tint Base TC

<b>Product codes:</b>	117-2705 Flat 117-2720 Low Gloss 117-2735 Satin 117-2790 High Gloss	<b>Viscosity</b>	Zahn #2 signature cup 28-30 sec at 25°C
		<b>Flash Point:</b>	12°C (53.6° F)
		<b>Density (kg/l):</b>	0.96
		<b>Solid (% by weight):</b>	38.62%
		<b>Solid (% by volume):</b>	30.45%
		<b>Shelf Life (months):</b>	12

### Product Description:

CHEMLIFE 24 PLUS Clear Tint Base TC is a complementary product to the CHEMLIFE 24 PLUS series for use when deep dark colors are desired. This tinting base has excellent color stability and delivers a silky feel and aesthetically pleasing look. Provides excellent sprayability and flow with outstanding vertical hang, hardness and durability. Like the other CHEMLIFE 24 products it has a 24 hour potlife.

Special Recognition: Meets Kitchen Cabinet Manufacturer Association (KCMA) Standards.

Recommended: Meets Architectural Woodwork Institute (AWI), System 5 performance standard for chemical and moisture resistance.

### Uses:

This product is recommended for kitchen cabinets, high build office or residential furniture as well as other interior wood applications.

<b>Environmental Data (as supplied):</b>	<b>VOC less exempt lb/gal:</b>	<4.10
	<b>VOC lb/gal:</b>	<4.10
	<b>VOC less exempt g/l:</b>	
	<b>VOC g/l:</b>	
	<b>VOC lb/lb Solid:</b>	<0.70
	<b>VHAPs lb/lb Solid:</b>	<0.25


### Note:

N/A

<b>Application Data</b>	<b>Suggested Uses:</b>	Wood Finish
	<b>Mixing Ratio:</b>	10% 873-1251
	<b>Suggested Uses:</b>	24 hours
	<b>Application Viscosity:</b>	Zahn #2 signature cup 28-30 seconds
	<b>Reducer:</b>	121-8020 or 121-803
	<b>Retarder:</b>	800-5328 EEP
	<b>Clean-up Solvent:</b>	Lacquer Thinner
	<b>Recommended Wet Film:</b>	3 - 5 mils
	<b>Coverage:</b>	488 sq. ft / gal at 1 mil dry and 100% transfer efficiency. Coverage will vary depending on method of application or coating thickness.

### Note:

N/A



Directions for use:

**Surface Preparation:**

Substrate must be sanded using 120 or 150 grit stearated paper prior to staining or coating. Sealers, if used, should be sanded with 240, 280 and 320 grit stearated paper prior to being coated. The substrate as well as the sealers should be topcoated within eight hours of being sanded. CHEMLIFE 24 PLUS Tint Base TC cannot be used on metal, old oil or cellulose lacquers. Stain systems used under acid catalyzed systems should be acid stable.

**General Information:**

Catalyze and reduce the material as recommended. CHEMLIFE 24 PLUS Tint Base TC is applied in one to two coats on all kinds of wood meant for indoor use. Thorough sanding between the coats is a must for good adhesion. The second and subsequent coats must be applied the same day as the previous coat is sanded.

Contact with metal surfaces should be avoided once the CHEMLIFE 24 PLUS Tint Base TC has been catalyzed. To ensure proper sheen, the catalyzed material should be agitated at all times.

This product can be used as a self-sealer. Appropriate sealer is Chemlife 24 Conversion Varnish Sealer 421-6300 or CHEMLIFE 24 PLUS Conversion Varnish Primer 522-2500 or 522-2501. Consult with your coatings supplier for specific recommendations.

CHEMLIFE 24 PLUS Tint Base TC demonstrates excellent resistance to marring, dry heat, moisture, household and office liquids, etc. When this product is used as its own sealer, its special formulation ensures excellent filling and easy sanding properties with superior holdout for subsequent coating. CHEMLIFE 24 PLUS Tint Base TC must be thoroughly stirred, while adding catalyst and reducer in the recommended ratio. Total recommended film build of the Chemlife system should not exceed 4 mils dry.

CHEMLIFE 24 PLUS Tint Base TC must not be polluted with oil and must not be sanded with steel wool between coats.

CHEMLIFE 24 PLUS Tint Base TC must not be used and dried at temperatures below 18°C or relative humidity above 65%.

During the curing process, the coating must not be exposed to ammonia vapors. Ammonia cleaners should not be used for cleaning the finished surface. This may accelerate discoloration.

THE CUSTOMER IS RESPONSIBLE FOR FOLLOWING THE RECOMMENDED APPLICATION PROCEDURES. FAILURE TO ADHERE TO THE RECOMMENDATIONS GIVEN IN THIS DATA SHEET WILL LIKELY RESULT IN UNSATISFACTORY FILM APPEARANCE OR FILM FAILURE. THE COMPLETE COATING SYSTEM SHOULD BE CHECKED FOR REQUIRED PROPERTIES PRIOR TO THE START-UP OF PRODUCTION

**Drying Times:**

	Room Temperature (20°C / 68°F)	Forced Drying Schedule (50°C / 122°F)
<b>Tack Free Time:</b>	15 minutes	Flash off before entering oven
<b>Dry to Sand:</b>	1 hour	Overnight
<b>Dry to Stack:</b>	30 minutes	3 hours

**Note:**

N/A

Dry times are greatly affected by film build, porosity of substrate, air movement as well as heat and humidity. Temperatures are based on actual board temperature. This may vary depending on length of time for boards to reach these temperatures. Minimum curing temperatures of 64°F/18°C must be maintained throughout the curing cycle to achieve the film integrity as stated in product features.

These products are designed for industrial use only. AkzoNobel views safety as a top priority. Please refer to Material Safety Data Sheet for information on the safe use of this product.

Values shown are calculated estimates and should not be construed as product specifications. We cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and users assume all responsibility and liability for loss or damage arising from the use of our products whether used alone or a combination with other products. Use of unapproved or reclaimed solvent blends may reduce film properties and is not recommended.

Akzo Nobel Coatings, Inc  
1431 Progress Ave  
High Point, NC 27260  
336-841-5111

Updated: 2024-05-19 01:00:27

Copyright 2021 AkzoNobel. All Rights Reserved. Chemcraft is a registered trademark of Akzo Nobel Coatings Inc.