

431-1219 E.S. HS Sealer

Product codes: 431-1219 E.S. HS Sealer	Viscosity	Zahn #2 signature cup 22 sec at 25°C
	Flash Point:	-3°C (26°F)
	Density (kg/l):	0.94 ± 2% at 25°C
	Solid (% by weight):	28%
	Solid (% by volume):	20%
	Shelf Life (months):	6

Product Description:

?E.S. HS Sealer is a one-component, pre-catalyzed sealer designed for all types for all types of woods for interior use. It is rapid dry and sands easily to a smooth finish. This particular product is developed to have higher solids than our standard E.S. Sealer while maintaining the same ease of use.

Uses:

Used as a protective coating for wood. For interior uses only.

Environmental Data (as supplied):

VOC less exempt lb/gal:	<2.26
VOC lb/gal:	<0.8
VOC less exempt g/l:	
VOC g/l:	
VOC lb/lb Solid:	<0.24
VHAPs lb/lb Solid:	<0.10

Note:

See individual compliance sheets for specific data

Application Data

Suggested Uses:	Spray
Mixing Ratio:	N/A
Suggested Uses:	N/A
Application Viscosity:	18-24 sec Zahn #2 at 25°C
Reducer:	Lacquer Thinner
Retarder:	N/A
Clean-up Solvent:	Lacquer Thinner
Recommended Wet Film:	3 - 5 wet mils
Coverage:	N/A

Note:

N/A

Directions for use:

Surface Preparation:

Wood must be sanded with a #120, 150 or 180 grit paper and free of dust and all contaminants. Sealer must be sanded with a #280/320 paper and the topcoat must be applied within 8 hours after the sanding. Stain systems under acid containing coatings should be acid stable.

General Information:

Apply 1 or 2 coats of 3 to 5 mils wet and allow 30-45 minutes dry at 20° C prior to sanding and applying next coating. A thorough sanding with 280/320 grit paper of each coat is essential for proper adhesion. Eliminate all contact with metallic surfaces. Maximum film build of the topcoat should not exceed 2 mils dry. Maximum film build of the system should not exceed 4 mils dry.

431-1219 is used under pre-catalyzed following topcoat: 431-90XX and 431-98XX (355-8XX).

To obtain complete cure, E.S. HS Sealer should be applied at a temperature above 18°C and relative humidity below 65%. When drying, this product is not to be exposed to ammonia vapours. Finished surfaces must not be cleaned with ammonia containing products. Always use plastic or stainless equipment to eliminate discoloration due to oxidation.

THE CUSTOMER IS RESPONSIBLE FOR FOLLOWING THE RECOMMENDED APPLICATION PROCEDURES. FAILURE TO ADHERE TO THE RECOMMENDATIONS GIVEN IN THIS DATA SHEET WILL LIKELY RESULT IN UNSATISFACTORY FILM APPEARANCE OR FILM FAILURE. THE COMPLETE COATING SYSTEM SHOULD BE CHECKED FOR REQUIRED PROPERTIES PRIOR TO THE START-UP OF PRODUCTION

Drying Times:

	Room Temperature (20°C / 68°F)	Forced Drying Schedule (50°C / 122°F)
Tack Free Time:	15 - 20 minutes	Flash off before entering oven
Dry to Sand:	45 - 60 minutes	2 - 3 hours
Dry to Stack:	15 - 20 minutes	20 – 30 minutes

Note:

N/A

Dry times are greatly affected by film build, porosity of substrate, air movement as well as heat and humidity. Temperatures are based on actual board temperature. This may vary depending on length of time for boards to reach these temperatures. Minimum curing temperatures of 64°F/18°C must be maintained throughout the curing cycle to achieve the film integrity as stated in product features.

These products are designed for industrial use only. AkzoNobel views safety as a top priority. Please refer to Material Safety Data Sheet for information on the safe use of this product.

Values shown are calculated estimates and should not be construed as product specifications. We cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and users assume all responsibility and liability for loss or damage arising from the use of our products whether used alone or a combination with other products. Use of unapproved or reclaimed solvent blends may reduce film properties and is not recommended.

Akzo Nobel Coatings, Inc
 1431 Progress Ave
 High Point, NC 27260
 336-841-5111

Updated: 2024-05-20 01:00:33

Copyright 2021 AkzoNobel. All Rights Reserved. Chemcraft is a registered trademark of Akzo Nobel Coatings Inc.