

436-47XX Selva™ Pro Acrilico Clear Acrylic Topcoat

Product codes:	436-4705 Flat	Viscosity	Zahn #2 signature cup 20-24 sec at 25° C	
	436-4710 Matte			
	436-4725 Low Gloss		Flash Point:	25° C
	436-4735 Satin		Density (kg/l):	0.84
	436-4750 Semi-Gloss		Solid (% by weight):	22.9 +/-2
	436-4790 High Gloss		Solid (% by volume):	17.9 +/-2
		Shelf Life (months):	24	

Product Description:

Acrilico is formulated with crystal clarity and no discoloration. Acrilico takes acrylic polyurethane coating to a new level. While providing a great look for open pore finishes, Acrilico is also the logical choice for the high end kitchen cabinet industry. The Acrilico line provides superior surface resistance.

Uses:

Acrilico is designed to use on high end woodwork such as interior marine and aircraft, cabinetry, store fixtures, expensive veneers, and musical instruments. Great choice for surfaces that require extra chemical resistance.

Environmental Data (as supplied):	VOC less exempt g/l:	728 +/-5%
	VOC g/l:	728 +/-5%

Note:

N/A

Application Data	Suggested Uses:	Wood Finishes
	Mixing Ratio:	100 Parts 436-47XX with 10 Parts 876-9102 (by volume)
	Suggested Uses:	4 hours
	Application Viscosity:	Zahn #2 signature cup 20-24 seconds.
	Reducer:	803-2000
	Retarder:	800-2001 3-5% by volume
	Clean-up Solvent:	800-5500 Acetone
	Recommended Wet Film:	4-6 wet mils
	Coverage:	N/A

Note:

MAXIMUM DRY FILM THICKNESS OF THE SYSTEM MUST NOT EXCEED 4 DRY MILS

Directions for use:**Surface Preparation:**

Substrate must be sanded using 120, 150 or 180 grit paper prior to staining or coating. Sealer should be sanded with 280/320 grit paper prior to being coated. The sealer should be coated within eight hours of being sanded. Appropriate sealer is the Selva Pro Acrilico Sealer 436-4700. When recoating, the previous coat of Acrilico must be sanded and the next coat applied within eight hours. Stain systems used under Acrilico are formulated to develop excellent grain definition. AkzoNobel recommends using Promatch® W/B Monocolor Spray Stains 824-50XX, Promatch Aqua Stains 824-51XX, Promatch Dye Stains 890-85XX or Promatch C-Mix Wipe Stains 825-90XX, 825-91XX.

General Information:

The mixed product contains 876-9102, an isocyanate based co-reactant. Please follow all precautions associated with handling and use of those materials. Refer to MSDS for detail information. Oil stains must be avoided because they will interfere with the adhesion. When coating exotic woods (Teak, Rosewood, etc.) a barrier coat (tie-coat) should be applied before the sealer or base coat. See Product data sheet for 420-1205

Isolante.

Product must be thoroughly stirred before adding the hardener in the recommended ratio. The viscosity of the product should be monitored after mixing with the hardener. The relative humidity in the application and drying room should not exceed 75% for maximum coating performance.

THE CUSTOMER IS RESPONSIBLE FOR FOLLOWING THE RECOMMENDED APPLICATION PROCEDURES. FAILURE TO ADHERE TO THE RECOMMENDATIONS GIVEN IN THIS DATA SHEET WILL LIKELY RESULT IN UNSATISFACTORY FILM APPEARANCE OR FILM FAILURE. THE COMPLETE COATING SYSTEM SHOULD BE CHECKED FOR REQUIRED PROPERTIES PRIOR TO THE START-UP OF PRODUCTION

Drying Times:

	Room Temperature (20°C / 68°F)	Forced Drying Schedule (50°C / 122°F)
Tack Free Time:	30 minutes	15-20 minutes
Dry to Sand:	2 hours	30 minutes
Dry to Stack:	24 hours	1 hour

Note:

N/A

Dry times are greatly affected by film build, porosity of substrate, air movement as well as heat and humidity. Temperatures are based on actual board temperature. This may vary depending on length of time for boards to reach these temperatures. Minimum curing temperatures of 64°F/18°C must be maintained throughout the curing cycle to achieve the film integrity as stated in product features.

These products are designed for industrial use only. AkzoNobel views safety as a top priority. Please refer to Material Safety Data Sheet for information on the safe use of this product.

Values shown are calculated estimates and should not be construed as product specifications. We cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and users assume all responsibility and liability for loss or damage arising from the use of our products whether used alone or a combination with other products. Use of unapproved or reclaimed solvent blends may reduce film properties and is not recommended.

Akzo Nobel Coatings, Inc
1431 Progress Ave
High Point, NC 27260
336-841-5111

Updated: 2024-11-07 01:00:45

Copyright 2021 AkzoNobel. All Rights Reserved. Chemcraft is a registered trademark of Akzo Nobel Coatings Inc.