

824-17XX Promatch® Aqua Dry Glaze WB Stain

| | | | |
|-----------------------|----------------------|-----------------------------|-----------------|
| Product codes: | 824-1700 WB Pickling | Viscosity | N/A |
| | Dust Neutral | Flash Point: | 93.1°C (200° F) |
| | 824-1723 WB Pickling | Density (kg/l): | 1.16-1.24 |
| | Dust Blood Red | Solid (% by weight): | 18-51 |
| | 824-1724 WB Pickling | Solid (% by volume): | 8-28 |
| | Dust Yellow | Shelf Life (months): | 6 |
| | 824-1725 WB Pickling | | |
| | Dust Brown | | |
| | 824-1726 WB Pickling | | |
| | Dust White | | |
| | 824-1728 WB Pickling | | |
| | Dust Black | | |
| | 824-1732 WB Pickling | | |
| | Dust Burnt Umber | | |

Product Description:

Promatch Aqua Dry Glaze is an intermix system designed to create specialty finishes. The intermix system is available in 4 rich colors and a neutral base. The neutral base can be used to reduce strength.

Uses:

Excess glaze can be removed with an abrasive pad or dry rag wiping in one direction for specific desired look. Aqua Dry Glaze is to be used in Waterborne system only, the use in combination with acid cured system is not recommended.

| | | |
|--|--------------------------------|------|
| Environmental Data (as supplied): | VOC less exempt lb/gal: | <5.6 |
| | VOC lb/gal: | <5.6 |
| | VOC less exempt g/l: | |
| | VOC g/l: | |
| | VOC lb/lb Solid: | <1.6 |
| | VHAPs lb/lb Solid: | <0.3 |

Note:

N/A

| | | |
|-------------------------|-------------------------------|------------------------|
| Application Data | Suggested Uses: | As a monocolour system |
| | Mixing Ratio: | N/A |
| | Suggested Uses: | N/A |
| | Application Viscosity: | N/A |
| | Reducer: | Water |
| | Retarder: | N/A |
| | Clean-up Solvent: | Water |
| | Recommended Wet Film: | N/A |
| | Coverage: | N/A |

Note:

N/A

Directions for use:

Surface Preparation:

Substrate must be sanded using 120, 150 or 180 grit paper prior to staining.

General Information:

N/A

THE CUSTOMER IS RESPONSIBLE FOR FOLLOWING THE RECOMMENDED APPLICATION PROCEDURES. FAILURE TO ADHERE TO THE RECOMMENDATIONS GIVEN IN THIS DATA SHEET WILL LIKELY RESULT IN UNSATISFACTORY FILM APPEARANCE OR FILM FAILURE. THE COMPLETE COATING SYSTEM SHOULD BE CHECKED FOR REQUIRED PROPERTIES PRIOR TO THE START-UP OF PRODUCTION

Drying Times:

| | Room Temperature (20°C / 68°F) | Forced Drying Schedule (50°C / 122°F) |
|-----------------|-----------------------------------|--|
| Tack Free Time: | N/A | N/A |
| Dry to Sand: | N/A | N/A |
| Dry to Stack: | N/A | N/A |

Note:

N/A

Dry times are greatly affected by film build, porosity of substrate, air movement as well as heat and humidity. Temperatures are based on actual board temperature. This may vary depending on length of time for boards to reach these temperatures. Minimum curing temperatures of 64°F/18°C must be maintained throughout the curing cycle to achieve the film integrity as stated in product features.

These products are designed for industrial use only. AkzoNobel views safety as a top priority. Please refer to Material Safety Data Sheet for information on the safe use of this product.

Values shown are calculated estimates and should not be construed as product specifications. We cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and users assume all responsibility and liability for loss or damage arising from the use of our products whether used alone or a combination with other products. Use of unapproved or reclaimed solvent blends may reduce film properties and is not recommended.

Akzo Nobel Coatings, Inc
1431 Progress Ave
High Point, NC 27260
336-841-5111