

## 825-3503 Chemfill Neutral

<b>Product codes:</b>	825-3503 Chemfill Neutral	<b>Viscosity</b>	30 000-40 000 CPS @25°C
		<b>Flash Point:</b>	27°C
		<b>Density (kg/l):</b>	1.52 ± 2% at 25°C
		<b>Solid (% by weight):</b>	88%
		<b>Solid (% by volume):</b>	78%
		<b>Shelf Life (months):</b>	6

**Product Description:**  
All purpose filler for furniture and cabinets.

**Uses:**  
For interior use only.

<b>Environmental Data (as supplied):</b>	<b>VOC less exempt lb/gal:</b>	<4.7
	<b>VOC lb/gal:</b>	<4.7
	<b>VOC less exempt g/l:</b>	
	<b>VOC g/l:</b>	
	<b>VOC lb/lb Solid:</b>	<1.3
	<b>VHAPs lb/lb Solid:</b>	<0.01

**Note:**  
See individual compliance sheets for specific data.

<b>Application Data</b>	<b>Suggested Uses:</b>	By spray or with a cloth
	<b>Mixing Ratio:</b>	N/A
	<b>Suggested Uses:</b>	N/A
	<b>Application Viscosity:</b>	N/A
	<b>Reducer:</b>	20-25% 801-1202(Varsol) or 800-4310(Solvent G) if applied by spray
	<b>Retarder:</b>	N/A
	<b>Clean-up Solvent:</b>	Lacquer Thinner
	<b>Recommended Wet Film:</b>	2 - 4 mils wet
	<b>Coverage:</b>	N/A

**Note:**  
N/A

**Directions for use:**

**Surface Preparation:**

The substrate must be sanded with a 120, 150 or 180 grit sand paper and free of dust and all contaminants.

**General Information:**

Mix well before usage. Hard settling can occur due to heavy solids content. Apply by spray after dilution or with a cloth. After 5 minutes of drying, wipe clean with a cloth in a circular motion. Allow to dry for 4 hours before applying the subsequent coat. Reduce product will settle quickly.

To obtain complete cure, system should be applied at a temperature above 18°C and relative humidity below 65%.

THE CUSTOMER IS RESPONSIBLE FOR FOLLOWING THE RECOMMENDED APPLICATION PROCEDURES. FAILURE TO ADHERE TO THE RECOMMENDATIONS GIVEN IN THIS DATA SHEET WILL LIKELY RESULT IN UNSATISFACTORY FILM APPEARANCE OR FILM FAILURE. THE COMPLETE COATING SYSTEM SHOULD BE CHECKED FOR REQUIRED PROPERTIES PRIOR TO THE START-UP OF PRODUCTION

**Drying Times:**

	<b>Room Temperature (20°C / 68°F)</b>	<b>Forced Drying Schedule (50°C / 122°F)</b>
<b>Tack Free Time:</b>	4 hours	N/A
<b>Dry to Sand:</b>	N/A	N/A
<b>Dry to Stack:</b>	N/A	N/A

**Note:**

N/A

Dry times are greatly affected by film build, porosity of substrate, air movement as well as heat and humidity. Temperatures are based on actual board temperature. This may vary depending on length of time for boards to reach these temperatures. Minimum curing temperatures of 64°F/18°C must be maintained throughout the curing cycle to achieve the film integrity as stated in product features.

These products are designed for industrial use only. AkzoNobel views safety as a top priority. Please refer to Material Safety Data Sheet for information on the safe use of this product.

Values shown are calculated estimates and should not be construed as product specifications. We cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and users assume all responsibility and liability for loss or damage arising from the use of our products whether used alone or a combination with other products. Use of unapproved or reclaimed solvent blends may reduce film properties and is not recommended.

Akzo Nobel Coatings, Inc  
1431 Progress Ave  
High Point, NC 27260  
336-841-5111

Updated: 2024-05-20 01:00:27

Copyright 2021 AkzoNobel. All Rights Reserved. Chemcraft is a registered trademark of Akzo Nobel Coatings Inc.