

## 117-19XX Plasticolor 275 White Post-Cat Pigmented TC

<b>Product codes:</b>	117-1920 Low Gloss	<b>Viscosity</b>	Zahn #2 signature cup 15 sec at 77°F
	117-1940 Satin	<b>Flash Point:</b>	-4°F (-20°C)
		<b>Density (lb/gal):</b>	9.1
		<b>Solid (% by weight):</b>	54%
		<b>Solid (% by volume):</b>	39%
		<b>Shelf Life (months):</b>	12

### Product Description:

Plasticolor 275 White is a two-component high solids post-catalyzed Reactive Amino Coating (RAC) topcoat. This product has been formulated to meet 275 g/l VOC regulations. Plasticolor 275 White gives a smooth, tough and hardwearing surface resisting influence from alcohol, water, etc. Plasticolor 275 White has very good light stability based on the type of resin used. Special Recognition: When applied as specified will meet required performance for the ANSI/KCMA A161.1 2000 9.0 Finish tests. Recommended: Architectural Woodwork Institute, (8<sup>th</sup> Ed) - Conversion Varnish Opaque

### Uses:

It is used as the final coat over wood, plywood, chipboard, etc., meant for interior use. This product is recommended for kitchen cabinets, high build office or residential furniture as well as many other interior wood applications where high build and durability are required.

<b>Environmental Data (as supplied):</b>	<b>VOC less exempt lb/gal:</b>	<2.10
	<b>VOC lb/gal:</b>	<0.85
	<b>VOC less exempt g/l:</b>	
	<b>VOC g/l:</b>	
	<b>VOC lb/lb Solid:</b>	<0.20
	<b>VHAPs lb/lb Solid:</b>	<0.01

### Note:

See individual compliance sheets for specific data

<b>Application Data</b>	<b>Suggested Uses:</b>	Wood Finish
	<b>Mixing Ratio:</b>	100 parts 117-19XX to 5 parts 873-1900
	<b>Suggested Uses:</b>	8 hours
	<b>Application Viscosity:</b>	Zahn #2 signature cup 14 – 15 seconds
	<b>Reducer:</b>	800-5500
	<b>Retarder:</b>	800-5328
	<b>Clean-up Solvent:</b>	800-5500
	<b>Recommended Wet Film:</b>	3 – 5 mils
	<b>Coverage:</b>	N/A

### Note:

N/A

**Directions for use:****Surface Preparation:**

Primer should be sanded using 240 and 320 grit steared paper. A suitable primer is **catalyzed** Versaprime® 275 545-5120. Primers should be topcoated within eight hours of sanding. Care should be taken during sanding to avoid sanding through the primer. Substrate should be sanded using 120, 150 or 180 grit steared paper prior to coating. Plasticolor 275 White cannot be used on metal, old oil or cellulose lacquers.

**General Information:**

Agitate material before use. Catalyze and reduce the material as recommended. Always mix Plasticolor 275 White while adding hardener and reducers in the recommended mixing ratios. Plasticolor 275 White must be agitated thoroughly at all times to ensure product consistency and gloss.

Apply at 3-5 mils wet on sanded substrate. Further coats may be applied after complete drying followed by sanding with 280/320 grit steared paper. A thorough sanding between the coats is essential to the adhesion. The second and subsequent coats must be applied the same day as the previous coat is sanded.

Maximum film build of Plasticolor 275 White should not exceed 4 mils dry. Maximum film build of total coating system must not exceed 6 mils dry. Contact with metal surfaces should be avoided.

Plasticolor 275 White must not be polluted with oil, varnish or the like and must not be sanded with steel wool between the coats.

Plasticolor 275 White must not be used and dried at temperatures below 64°F or relative humidity above 65%. During the curing process, the coating must not be exposed to ammonia vapors. Ammonia cleaners should not be used for cleaning the finished surface. This may accelerate discoloration.

Please note that, as with any other acid catalyzed product, this material contains, and has the potential to emit, formaldehyde (CAS# 50-00-0). As per the US Department of Labor Standard 29 CFR 1910.1048 covering formaldehyde, section (d)(1)(i) states that "Each employer who has a workplace covered by this standard shall monitor employees to determine their exposure to formaldehyde." Please refer to the OSHA web site at [www.osha.gov](http://www.osha.gov) for further information.

THE CUSTOMER IS RESPONSIBLE FOR FOLLOWING THE RECOMMENDED APPLICATION PROCEDURES. FAILURE TO ADHERE TO THE RECOMMENDATIONS GIVEN IN THIS DATA SHEET WILL LIKELY RESULT IN UNSATISFACTORY FILM APPEARANCE OR FILM FAILURE. THE COMPLETE COATING SYSTEM SHOULD BE CHECKED FOR REQUIRED PROPERTIES PRIOR TO THE START-UP OF PRODUCTION

**Drying Times:**

	<b>Room Temperature (20°C / 68°F)</b>	<b>Forced Drying Schedule (50°C / 122°F)</b>
<b>Tack Free Time:</b>	15 – 20 minutes	Flash off before entering oven
<b>Dry to Sand:</b>	3 hours	Overnight
<b>Dry to Stack:</b>	30 minutes	60 - 90 minutes

**Note:**

N/A

Dry times are greatly affected by film build, porosity of substrate, air movement as well as heat and humidity. Temperatures are based on actual board temperature. This may vary depending on length of time for boards to reach these temperatures. Minimum curing temperatures of 64°F/18°C must be maintained throughout the curing cycle to achieve the film integrity as stated in product features.

These products are designed for industrial use only. AkzoNobel views safety as a top priority. Please refer to Material Safety Data Sheet for information on the safe use of this product.

Values shown are calculated estimates and should not be construed as product specifications. We cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and users assume all responsibility and liability for loss or damage arising from the use of our products whether used alone or a combination with other products. Use of unapproved or reclaimed solvent blends may reduce film properties and is not recommended.

Akzo Nobel Coatings, Inc  
1431 Progress Ave  
High Point, NC 27260  
336-841-5111

Updated: 2024-05-17 01:00:22

Copyright 2021 AkzoNobel. All Rights Reserved. Chemcraft is a registered trademark of Akzo Nobel Coatings Inc.