

AQUASILK UNI PW WHITE PRIMER 550-3500

Product codes: N/A	Viscosity	600 - 700 cP (25°C)
	Flash Point:	> 200°F
	Density (lb/gal):	11.37
	Solid (% by weight):	54.86
	Solid (% by volume):	38.20
	Shelf Life (months):	12

Product Description:

AQUASILK UNI PW WHITE PRIMER has excellent blocking, filling and hiding properties. Excellent leveling, easy to sand, and superior holdout. AQUASILK UNI PW WHITE PRIMER has unique chemistry that provides excellent moisture resistance. Waterborne color system available utilizing 897 colorants at a maximum 7%.

Uses:

This AQUASILK UNI PW WHITE PRIMER is designed for cabinets, architectural millwork, furniture and refinish markets.

Environmental Data (as supplied):	VOC less exempt lb/gal:	1.16
	VOC lb/gal:	0.52
	VOC less exempt g/l:	139
	VOC g/l:	63.0
	VOC lb/lb Solid:	0.08
	VHAPs lb/lb Solid:	0.00

Note:

N/A

Application Data	Suggested Uses:	For Cabinet, Architectural millwork, refinish markets
	Mixing Ratio:	N/A
	Suggested Uses:	N/A
	Application Viscosity:	30 - 35 s Zahn signature #4
	Reducer:	Water up to 10% by volume depending on spray equipment
	Retarder:	803-1462 1 to 3% by volume as needed
	Clean-up Solvent:	Water
	Recommended Wet Film:	4 - 6 wet mils
	Coverage:	615.6 sqft/gal

Note:

N/A

Directions for use:

Surface Preparation:

Substrate must be sanded using 120, 150 or 180 grit paper prior to prime. AQUASILK UNI PW WHITE PRIMER should be sanded with 280/320 grit paper prior to being coated, The AQUASILK UNI PW WHITE PRIMER should be coated within eight hours of being sanded.

General Information:

N/A

THE CUSTOMER IS RESPONSIBLE FOR FOLLOWING THE RECOMMENDED APPLICATION PROCEDURES. FAILURE TO ADHERE TO THE RECOMMENDATIONS GIVEN IN THIS DATA SHEET WILL LIKELY RESULT IN UNSATISFACTORY FILM APPEARANCE OR FILM FAILURE. THE COMPLETE COATING SYSTEM SHOULD BE CHECKED FOR REQUIRED PROPERTIES PRIOR TO THE START-UP OF PRODUCTION

Drying Times:

	Room Temperature (20°C / 68°F)	Forced Drying Schedule (50°C / 122°F)
Tack Free Time:	15 minutes	10 minutes
Dry to Sand:	45 minutes	24 hours
Dry to Stack:	30 minutes	60 minutes

Note:

N/A

Dry times are greatly affected by film build, porosity of substrate, air movement as well as heat and humidity. Temperatures are based on actual board temperature. This may vary depending on length of time for boards to reach these temperatures. Minimum curing temperatures of 64°F/18°C must be maintained throughout the curing cycle to achieve the film integrity as stated in product features.

These products are designed for industrial use only. AkzoNobel views safety as a top priority. Please refer to Material Safety Data Sheet for information on the safe use of this product.

Values shown are calculated estimates and should not be construed as product specifications. We cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and users assume all responsibility and liability for loss or damage arising from the use of our products whether used alone or a combination with other products. Use of unapproved or reclaimed solvent blends may reduce film properties and is not recommended.

Akzo Nobel Coatings, Inc
1431 Progress Ave
High Point, NC 27260
336-841-5111

Updated: 2026-09-24 08:21:20

Copyright 2021 AkzoNobel. All Rights Reserved. Chemcraft is a registered trademark of Akzo Nobel Coatings Inc.